



## Fawori Marin Yacht Varnish

### PRODUCT DESCRIPTION

Urethane alkyd resin combination-based yacht varnish providing a superior finish with high gloss.

### SPECIFICATIONS

Protects the wood for long time thanks to the U.V. absorbents in its structure. Non-yellowing. Does not change the color of the wood due to its transparent quality. An interior and exterior varnish that preserves its natural look against atmospheric conditions, moisture and water, and adheres perfectly. Saves time and labor with its perfect spreading power.

### APPLICATION SURFACES

Fawori Marin Yacht Varnish is a UV-resistant gloss varnish that you can use comfortably on wood surfaces of vessels and on all kinds of wooden interior and exterior surfaces of buildings for decorative and protective purposes.

### APPLICATION

Wooden surfaces on which Fawori Marine Yacht Varnish will be applied should be free of oil, dirt and swollen paint residues. Protect the wooden surfaces that will be varnished for the first time with wood impregnation material. It is recommended to apply Fawori Marine Yacht Varnish in 3 coats with an interval of one day by sanding between coats. Impregnation with an impregnation substance is recommended at the beginning of the application for longevity of wood. Apply the same number of coats in ongoing work. Ensure that the humidity of the application wood is not over 15%.

Ensure that the ambient and surface temperatures are between +5°C and +30°C during application and until the products are fully dried, and protect the surfaces against frost. Apply using a brush, roller or spray gun.

Equipment used must be cleaned with Fawori Synthetic Thinner immediately after application. Our products should be applied on substructure surfaces that are built in line with General Construction Specifications dated 30.06.2007 and with No. 26568. For MSDS and TDS forms providing information about application details, health-safety-handling risks and precautions, visit [www.fawori.com.tr](http://www.fawori.com.tr).

### Airless Spraying:

Pressure : 120-140 bar

Nozzle Angle: 50°

Nozzle Size (inch): 0.010"

Thinning: 10-20 % (Volume)

### THINNING

Thin using Fawori Synthetic Thinner by 10-20% for spray gun applications, by 5-10% for brush or roller applications. Note that problems such as blistering, shrinking, cracking and drying may occur when a different brand of thinner is used.

### DRYING TIME (at 20°C, 65% RH)

Touch dryness: 2 hours

Hard-dry: 12 hours (drying time may increase at higher relative humidity and lower temperature)

### CONSUMPTION

Can be applied on an area of 14-18 m<sup>2</sup> in a single coat with 1 Liter based on the type and absorbency of the wood. Color and consumption may vary depending on the wood type, surface state, number of coats and application method. Perform a controlled sample run to estimate the precise consumption amount.

### FLASH POINT

36°C

### STORAGE

It can be stored in its unopened package, in a cool and dry place, away from frost and direct sunlight. Close the lid air-tight immediately after application.

**PACKAGE**

12 Liter, 2,5 Liter, 0,75 Liter

**WARNING STATEMENT**

Hazard

**HAZARD STATEMENTS**

H226: Inflammable liquid and vapor.

H304 Fatal if inhaled or swallowed.

**PRECAUTIONARY STATEMENTS**

P101 If medical advice is needed, have the product container or label at hand.

P102 Keep out of reach of children.

P103 Read the label before use.

P210 Keep away from heat/sparks/flame/hot surfaces - No smoking.

P241:Use explosion proof electrical/ventilating/lighting/.../equipment.

P301+P310 IF SWALLOWED: CALL NATIONAL POISON CONSULTING CENTER AT 114/ a doctor.

P303+P361+P353 IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse your skin with water/shower.

P405: Store locked up.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.

**Hazard-determining components for labeling:** *solvent naphtha (petroleum), medium aliphatic*

**Pose No.**

Y.25.001/04

**Rate No.**

04,561/01

This technical sheet is prepared based on laboratory data at normal conditions. Consult technical personnel for details that are not provided above. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change the information provided.

**This product is manufactured by Betek A.Ş., with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.**

**Rev5 March 2020**