



# Fawori Synthetic Parquet Varnish

## PRODUCT DESCRIPTION

Single-component, modified urethane alkyd-based glossy parquet varnish.

## SPECIFICATIONS

High and permanent gloss. Does not damage the natural look of interior wood surfaces and does not cause color changes. Transparent. Non-yellowing and forms a hard film. Resistant against liquid household cleaners. Does not leave brush marks.

## APPLICATION SURFACES

A glass varnish that can be used safely on interior wood floors, stairs and parquets that require strength.

## APPLICATION

Ensure the application surface is dry enough and free from any dirt for Fawori Synthetic Parquet Varnish. Apply Fawori Cellulosic Filling Varnish first to the rough application surface. Clean with a scraper before and apply Betek Parquet Cellulosic Filling Varnish if the application surface was varnished before. Apply two or three coats of Fawori Synthetic Parquet Varnish on the smooth surface that is obtained. Wait 12 hours after each coat. The application area can be opened to foot traffic after waiting for a minimum of 24 hours. Ensure that the humidity of the application wood is not over 15%.

Ensure that the ambient and surface temperatures are between +5°C and +30°C during application and until the products are fully dried, and protect the surfaces against frost. Apply using a brush, roller or spray gun. Equipment used must be cleaned with Fawori Synthetic Thinner immediately after application. Our products should be applied on substructure surfaces that are built in line with General Construction Specifications dated 30.06.2007 and with No. 26568. For MSDS and TDS forms providing information about application details, health-safety-handling risks and precautions, visit [www.fawori.com.tr](http://www.fawori.com.tr).

## Airless Spraying:

Pressure	: 120-140 bar
Nozzle Angle	: 50°
Nozzle Size (inch)	: 0.010"
Thinning	: 10-15 % (by volume)

## THINNING

It is recommended to thin by 25% with Fawori Synthetic Thinner for first coat applications and by 10-15% for second and, if required, third coat applications. Note that problems such as blistering, shrinking, cracking and drying may occur when a different brand of thinner is used.

## DRYING TIME (at 20°C, 65% RH)

Hard-dry: 12 hours. Can be opened to foot traffic after 24 hours. Gains physical and chemical strength maximum 4 days later (the drying period may lengthen at higher relative humidity and lower temperature).

## CONSUMPTION

Can be applied on an area of 14-16 m<sup>2</sup> in a single coat with 1 Liter based on the type and absorbency of the wood. Color and consumption may vary depending on the wood type, surface state, number of coats and application method. Perform a controlled sample run to estimate the precise consumption amount.

## FLASH POINT

36°C

## STORAGE

It can be stored in a cool and dry environment in its unopened packaging protected against frost and direct sunlight. Close the lid air-tight immediately after application.



## **PACKAGING**

12 Liter, 2,5 Liter, 0,75 Liter

## **WARNING STATEMENT** *Danger* **HAZARD STATEMENTS**

H226: Inflammable liquid and vapor.

H304 Fatal if inhaled or swallowed.

H361: Suspected of damaging fertility or the unborn child

H373 May cause damage to organs through prolonged or repeated exposure.

## **PRECAUTIONARY STATEMENTS**

P101 If medical advice is needed, have the product container or label at hand.

P102 Keep out of reach of children. P103 Read label before use. P210 Keep away from heat/sparks/flame/hot surfaces - No smoking.

P241: Use explosion proof electrical/ventilating/lighting/.../equipment.

P301+P310 IF SWALLOWED: *CALL NATIONAL POISON CONSULTING CENTER AT 114/ a doctor.*

P303+P361+P353 IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse your skin with water/shower.

P405: Keep locked up.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.

**Hazard-determining components for labeling:** solvent naphtha (petroleum), medium aliphatic

## **Pose No.**

Y.25.001/07

## **Rate No.**

04,561/03

This technical sheet is prepared based on laboratory data at normal conditions. Consult technical personnel for details that are not provided above. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change the information provided.

**This product is manufactured by Betek A.Ş., holding the certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.**

**Rev5 March 2020**